## Beam Design

## 1. Beam Data

Load Type:	Uniform Dist. Load
Support:	Simple Beam
Beam Type:	Sawn Lumber
Species:	Douglas Fir-Larch
Grade:	DF No.2
Size:	2 x 12
Design Span (L):	19.75 ft.
Clear Span:	19.50 ft.
Total Span:	20.00 ft.
Bearing (lb):	3 in.
Quantity (N):	3

braced

1.15 dry

360|240

 $T \leq 100^{\circ}F$ 

Vertical

No No

Live Load:	80	plf
Dead Load:	60	plf
Selfweight:	237.5	lbs
Dist. Selfweight:	12.02	plf

240.5 lbs

2. Design Loads

Total Weight:

4. Design Assumptions and Notes

Code Standard:	IBC 2015, NDS 2015
Bending Stress:	Parallel to Grain
Notes:	

# 5. Adjustment Factors

3. Design Options

Lateral Support:

Load Duration:

Defl. Limits:

Exposure: Temperature:

Orientation:

Incised Lumber:

Rep. Members:

	Factor	Description		Fb	Ft	Fv	Fc	$F_{c\perp}$	E/E <sub>min</sub>	
	CD	Load Duration Facto	or	1.15	1.15	1.15	1.15	-	-	
	CM	Wet Service Factor		1 <sup>b</sup>	1	1	1 <sup>c</sup>	1	1	
	Ct	Temperature Factor	•	1	1	1	1	1	1	
	CL	Beam Stability Facto	or	1	-	-	-	-	-	
	CF	Size Factor		1	1	-	1	-	-	
	C <sub>fu</sub>	Flat Use Factor		1.2 <sup>d</sup>	-	-	-	-	-	
	Ci	Incising Factor		1	1	1	1	1	1	
	Cr	Repetitive Member Fac	ctor	1	-	-	-	-	-	
	a) Adjust	ment factors per AWC NDS 2015 ar	nd NDS 201	5 Supplem	ent.					
	b) When	$(F_b)(C_F) \le 1,150 \text{ psi}, C_M = 1.0.$								
	c) When	$(F_c)(C_F) \le 750 \text{ psi}, C_M = 1.0.$								
	d) Only a	pplies when sawn lumber or glulam	beams are	loaded in be	ending abou	t the y-y axi	s.			
Subject Beam Des	sign	Customer	Location							Job No. 2023A157
<sup>Engr.</sup> N. Wilker						Rev				
Date 4/14/202	23	3050 State Route 109 Copalis Beach, WA 98535 ph. (425) 741-5555 www.medeek.com				Copyright © 2014	Page 1			

### 6. Beam Calculations

Determine reference design values, sectional properties and self weight of beam:

$$A = b x d$$

$$S_x = \frac{bd^2}{6}, \ S_y = \frac{b^2d}{6}$$
  
 $I_x = \frac{bd^3}{12}, \ I_y = \frac{b^3d}{12}$ 

where:

b = Breadth of rectangular beam in bending (in.) d = Depth of rectangular beam in bending (in.) A = Cross sectional area of beam (in.<sup>2</sup>)  $S_x$  = Section modulus about the X-X axis (in.<sup>3</sup>)  $S_y$  = Section modulus about the Y-Y axis (in.<sup>3</sup>)  $I_x$  = Moment of inertia about the X-X axis (in.<sup>4</sup>)  $I_y$  = Moment of inertia about the Y-Y axis (in.<sup>4</sup>)

$$\begin{split} &b = 1.500 \text{ in.} \\ &d = 11.250 \text{ in.} \\ &A = 1.500 \text{ x } 11.250 = 16.88 \text{ in.}^2 \\ &S_x = (1.500)(11.250)^2/6 = 31.64 \text{ in.}^3 \\ &S_y = (1.500)^2(11.250)/6 = 4.22 \text{ in.}^3 \\ &I_x = (1.500)(11.250)^3/12 = 177.98 \text{ in.}^4 \\ &I_y = (1.500)^3(11.250)/12 = 3.16 \text{ in.}^4 \end{split}$$

Reference Design Values from Table 4A NDS Supplement (Reference Design Values for Visually Graded Dimension Lumber, 2" - 4" thick).

Species & Grade	Fb	Ft	Fv	$F_{c\perp}$	Fc	Е	Emin	G
DF No.2	900	575	180	625	1350	1600000	580000	0.5

The following formula shall be used to determine the density of wood (lbs/ft<sup>3</sup>. (NDS Supplement Sec. 3.1.3)

$$\rho_w = 62.4 \left[ \frac{G}{1 + G(0.009)(m.c)} \right] \left[ 1 + \frac{m.c.}{100} \right]$$

where:

 $\rho_w$  = Density of wood (lbs/ft<sup>3</sup>) G = Specific gravity of wood (dimensionless) m.c. = Moisture content of wood (percentile)

G = 0.5

m.c. = 19 % (Max. moisture content at dry service conditions)

Beam Design	Customer	Location		Job No. 2023A157
<sup>Engr.</sup> N. Wilkerson	MEDEEK ENGINE		This report may not be copied, reproduced or distributed without the written consent of Medeek Engineering Inc.	Rev. -
Date 4/14/2023	3050 State Route 109 Copa ph. (425) 741-5555 www.r		Copyright © 2014	Page 2


$$\rho_w = 62.4 \left[ \frac{0.5}{1 + 0.5(0.009)(19)} \right] \left[ 1 + \frac{19}{100} \right] = 34.20 \text{ lbs/ft}^3$$


 $\begin{aligned} \text{Volume}_{\text{total}} &= \text{N}[\text{A x } (\text{L} + \text{l}_{\text{b}})] = 3 \text{ x } [16.88 \text{ x } (237.00 + 3)] \text{ x } (12 \text{ in./ft.})^3 = 7.03 \text{ ft}^3 \\ \text{Volume}_{\text{span}} &= \text{N}[\text{A x } \text{L}] = 3 \text{ x } [16.88 \text{ x } 237.00] \text{ x } (12 \text{ in./ft.})^3 = 6.94 \text{ ft}^3 \end{aligned}$ 

Total Weight (W<sub>T</sub>) =  $\rho_W x$  Volume<sub>total</sub> = 34.20 x 7.03 = 240.5 lbs Self Weight (W<sub>S</sub>) =  $\rho_W x$  Volume<sub>span</sub> = 34.20 x 6.94 = 237.5 lbs

Distributed Self Weight (w<sub>s</sub>) =  $\frac{W_S}{L} = \frac{237.5}{19.75}$  = 12.02 plf

Load, Shear and Moment Diagrams:





#### 1.) Bending:

Members subject to bending stresses shall be proportioned so that the actual bending stress or moment shall not exceed the adjusted bending design value:

 $f_b \leq F_b' \ (\textit{NDS Sec. 3.3.1})$ 

where:

$$\label{eq:fb} \begin{split} f_b &= M \ / \ S \\ F_b' &= F_b(C_D)(C_M)(C_t)(C_L)(C_F)(C_i)(C_r) \end{split}$$

Beam is braced laterally along its compression edge. Laterial stability is not a consideration:

C<sub>L</sub> = Beam Stability Factor = 1.0

 $F_{bx'} = (900)(1.15)(1)(1)(1)(1)(1)(1) = 1035.0 \text{ psi}$ 

 $f_b = \frac{M}{N \times S_x} = \frac{88949}{3 \times 31.64} = 937.1 \text{ psi}$ 

 $f_b = 937.1 \ psi < F_{bx'} = 1035.0 \ psi \ (CSI = 0.91)$  ? OK

Subject Beam Design	Customer	Location			Job No. 2023A157
<sup>Engr.</sup> N. Wilkerson	MEDEEK ENGINEERING INC.				Rev. -
Date 4/14/2023	3050 State Route 109 Copa ph. (425) 741-5555 www.r	s Beach, WA 98535			Page 4

#### 2.) Shear:

Members subject to shear stresses shall be proportioned so that the actual shear stress parallel to grain or shear force at any cross section of the bending member shall not exceed the adjusted shear design value:

$$f_V \leq F_V'$$
 (NDS Sec. 3.4.1)

where:

$$\mathbf{f_v} = \frac{3V}{2A}$$

 $F_{v}' = F_{v}(C_{D})(C_{M})(C_{t})(C_{i})$ 

$$F_{vx}' = (180)(1.15)(1)(1)(1) = 207.00 \text{ psi}$$

Shear Reduction: For beams supported by full bearing on one surface and loads applied to the opposite surface, uniformly distributed loads within a distance, d, from supports equal to the depth of the bending member shall be pemitted to be ignored. For beams supported by full bearing on one surface and loads applied to the opposite surface, concentrated loads within a distance equal to the depth of the bending member shall be permitted to be multiplied by x/d where x is the distance from the beam support face to the load. See NDS 2015, Figure 3C.

$$f_v * = \frac{3V^*}{2(N \times A)} = \frac{3(1358.72)}{2(3 \times 16.88)} = 40.26 \text{ psi}$$

$$f_v^* = 40.26 \text{ psi} < F_{vx'} = 207.00 \text{ psi} (CSI = 0.19)$$
 ? OK

No Reduction in Shear (conservative):

$$\mathbf{f_{V}} \!=\! \frac{3V}{2(N \times A)} = \frac{3(1501.24)}{2(3 \times 16.88)} \!=\! \mathbf{44.48 \ psi}$$

 $f_v = 44.48 \ psi < F_{vx}' = 207.00 \ psi \ (CSI = 0.21) \ ? \ \textbf{OK}$ 

#### 3.) Deflection:

Bending deflections calculated per standard method of engineering mechanics for live load and total load:

#### LL Allowable: L/360 TL Allowable: L/240

 $E_x' = E_x(C_M)(C_t)(C_i) = 1600000(1)(1)(1) = 1600000 \text{ psi}$ 

Subject Beam Design	Customer	Location			Job No. 2023A157
<sup>Engr.</sup> N. Wilkerson	MEDEEK ENGINE		(Creation of the second s	This report may not be copied, reproduced or distributed without the written consent of Medeek Engineering Inc.	Rev. –
Date 4/14/2023	3050 State Route 109 Copa ph. (425) 741-5555 www.r			Copyright © 2014	Page 5

$$\Delta_{LL} = \frac{5w_{LL}L^4}{384E'_x(N \times I_x)} = \frac{5(80)(19.750)^4}{384(1600000)(3 \times 177.98)} \times \left(12\frac{in.}{ft.}\right)^3 = 0.32 \text{ in.}$$

$$(L/d)_{LL} = 237.00 / 0.32 = 739$$

$$\Delta_{LL} = 0.32 \text{ in} = L/739 < L/360 ? \text{OK}$$

$$\Delta_{TL} = \frac{5(w_{TL} + w_s)L^4}{384E'_x(N \times I_x)} = \frac{5(140 + 12.02)(19.750)^4}{384(1600000)(3 \times 177.98)} \times \left(12\frac{in.}{ft.}\right)^3 = 0.61 \text{ in.}$$

$$(L/d)_{TL} = 237.00 / 0.61 = 389$$

$$\Delta_{TL} = 0.61 \text{ in} = L/389 < L/240 ? \text{OK}$$

#### 4.) Bearing:

Members subject to bearing stresses perpendicular to the grain shall be proportioned so that the actual compressive stress perpendicular to grain shall be based on the net bearing area and shall not exceed the adjusted compression design value perpendicular to grain:

 $f_{c\perp} \leq F_{c\perp}$ ' (NDS Sec. 3.10.2)

where:

$$\mathbf{f_c}_{\perp} = \frac{R}{A_b}$$

 $F_{c\perp}' = F_{c\perp}(C_M)(C_t)(C_i)$ 

 $F_{c \perp x}' = (625)(1)(1)(1) = 625.00 \text{ psi}$ 

$$A_{b} = b x l_{b} = 1.5 x 3 = 4.50 in^{2}$$

$$f_{c\perp} = \frac{R}{N \times A_b} = \frac{1520.25}{3 \times 4.50} = 112.6 \text{ psi}$$

 $f_{c\,\perp} = 112.6 \; psi < F_{c\,\perp\,x'} = 625.00 \; psi \; (CSI = 0.18) \; ?$  OK

\*Disclaimer: The calculations produced herein are for initial design and estimating purposes only. The calculations and drawings presented do not constitute a fully engineered design. All of the potential load cases required to fully design an actual structure may not be provided by this calculator. For the design of an actual structure, a registered and licensed professional should be consulted as per IRC 2012 Sec. R802.10.2 and designed according to the minimum requirements of ASCE 7-10. The beam calculations provided by this online tool are for educational and illustrative purposes only. Medeek Design assumes no liability or loss for any designs presented and does not guarantee fitness for use.

Subject	Customer	Location		Job No.
Beam Design				2023A157
<sup>Engr.</sup> N. Wilkerson	MEDEEK ENGINE		This report may not be copied, reproduced or distributed without the written consent of Medeek Engineering Inc.	Rev. -
Date 4/14/2023	3050 State Route 109 Copa ph. (425) 741-5555 www.r	lis Beach, WA 98535 nedeek.com	Copyright © 2014	Page 6