# Beam Design

### 1. Beam Data

| Load Type:       | Uniform Dist. Load |
|------------------|--------------------|
| Support:         | Simple Beam        |
| Beam Type:       | Sawn Lumber        |
| Species:         | Southern Pine      |
| Grade:           | SP No.2            |
| Size:            | 2 x 10             |
| Design Span (L): | 11.75 ft.          |
| Clear Span:      | 11.50 ft.          |
| Total Span:      | 12.00 ft.          |
| Bearing (lb):    | 3 in.              |
| Quantity (N):    | 2                  |

| 2. Design Loads |
|-----------------|
|-----------------|

| Live Load:        | 100  | plf |
|-------------------|------|-----|
| Dead Load:        | 75   | plf |
| Selfweight:       | 84.5 | lbs |
| Dist. Selfweight: | 7.19 | plf |
| Total Weight:     | 86.3 | lbs |

## 3. Design Options

| Lateral Support: | braced                |
|------------------|-----------------------|
| Defl. Limits:    | 360 240               |
| Load Duration:   | 1.15                  |
| Exposure:        | dry                   |
| Temperature:     | $T \leq 100^{\circ}F$ |
| Orientation:     | Vertical              |
| T ' 1T 1         | N                     |
| Incised Lumber:  | No                    |

# 4. Design Assumptions and Notes

Code Standard: IBC 2015, NDS 2015 Bending Stress: Parallel to Grain Notes:

### 5. Adjustment Factors

|        | Factor            | Description                                   | Fb                  | Ft 1.15        | F <sub>v</sub> | F <sub>c</sub> | $F_{c\perp}$ | E/E <sub>min</sub> |         |
|--------|-------------------|---|---------------------|----------------|----------------|----------------|--------------|--------------------|---------|
|        | CD                | Load Duration Facto                           |                     | 1.15           | 1.15           | 1.15           | -            | -                  |         |
|        | CM                | Wet Service Factor                            | · 1 <sup>b</sup>    | 1              | 1              | 1 <sup>c</sup> | 1            | 1                  |         |
|        | Ct                | Temperature Factor                            | : 1                 | 1              | 1              | 1              | 1            | 1                  |         |
|        | CL                | Beam Stability Factor                         | or 1                | -              | -              | -              | -            | -                  |         |
|        | CF                | Size Factor                                   | 1                   | 1              | -              | 1              | -            | -                  |         |
|        | $C_{\mathrm{fu}}$ | Flat Use Factor                               | 1.2 <sup>d</sup>    | -              | -              | -              | -            | -                  |         |
|        | Ci                | Incising Factor                               | 1                   | 1              | 1              | 1              | 1            | 1                  |         |
|        | Cr                | Repetitive Member Fa                          | ctor 1              | -              | -              | -              | -            | -                  |         |
|        | a) Adjustn        | nent factors per AWC NDS 2015 an              | nd NDS 2015 Suppl   | ement.         |                |                |              |                    |         |
|        | b) When (         | $F_b)(C_F) \le 1,150 \text{ psi}, C_M = 1.0.$ |                     |                |                |                |              |                    |         |
|        | c) When (         | $F_c)(C_F) \le 750 \text{ psi}, C_M = 1.0.$   |                     |                |                |                |              |                    |         |
|        | d) Only ap        | pplies when sawn lumber or glulam             | beams are loaded in | n bending abou | ut the y-y ax  | is.            |              |                    |         |
|        |                   |   |                     |                |                |                |              |                    |         |
| ect    |                   | Customer                                      | Location            |                |                |                |              |                    | Job No. |
| Beam D | esign             |   |                     |                |                |                |              |                    | 2023    |

Engr. N. Wilkerson Date 1/12/2023

## MEDEEK ENGINEERING INC.

3050 State Route 109 Copalis Beach, WA 98535 ph. (425) 741-5555 www.medeek.com



witten consent of Engineering Inc. Page 1

Copyright © 2014

### 6. Beam Calculations

Determine reference design values, sectional properties and self weight of beam:

$$A = b x d$$

$$S_x = \frac{bd^2}{6}, \ S_y = \frac{b^2d}{6}$$
  
 $I_x = \frac{bd^3}{12}, \ I_y = \frac{b^3d}{12}$ 

where:

b = Breadth of rectangular beam in bending (in.)

d = Depth of rectangular beam in bending (in.)

A = Cross sectional area of beam (in.<sup>2</sup>)  $S_x$  = Section modulus about the X-X axis (in.<sup>3</sup>)  $S_y$  = Section modulus about the Y-Y axis (in.<sup>3</sup>)  $I_x$  = Moment of inertia about the X-X axis (in.<sup>4</sup>)  $I_y$  = Moment of inertia about the Y-Y axis (in.<sup>4</sup>)

$$\begin{split} &b = 1.500 \text{ in.} \\ &d = 9.250 \text{ in.} \\ &A = 1.500 \text{ x } 9.250 = 13.88 \text{ in.}^2 \\ &S_x = (1.500)(9.250)^2/6 = 21.39 \text{ in.}^3 \\ &S_y = (1.500)^2(9.250)/6 = 3.47 \text{ in.}^3 \\ &I_x = (1.500)(9.250)^3/12 = 98.93 \text{ in.}^4 \\ &I_y = (1.500)^3(9.250)/12 = 2.60 \text{ in.}^4 \end{split}$$

Reference Design Values from Table 4B NDS Supplement (Reference Design Values for Visually Graded Southern Pine Dimension Lumber, 2" - 4" thick). Values per March 2013 Addendum

| Species & Grade | Fb  | Ft  | $F_{v}$ | $F_{c\perp}$ | Fc   | Е       | Emin   | G    |
|-----------------|-----|-----|---------|--------------|------|---------|--------|------|
| SP No.2         | 800 | 475 | 175     | 565          | 1300 | 1400000 | 510000 | 0.55 |

The following formula shall be used to determine the density of wood (lbs/ft<sup>3</sup>. (NDS Supplement Sec. 3.1.3)

$$\rho_w = 62.4 \left[ \frac{G}{1 + G(0.009)(m.c)} \right] \left[ 1 + \frac{m.c.}{100} \right]$$

where:

 $\rho_w$  = Density of wood (lbs/ft<sup>3</sup>) G = Specific gravity of wood (dimensionless) m.c. = Moisture content of wood (percentile)

G = 0.55

 $m.c. = 19 \% \quad (\text{Max. moisture content at dry service conditions})$ 

| Subject<br>Beam Design        | Customer  | Location |  |   | Job No.<br>2023A2 |
|-------------------------------|---|----------|--|---|-------------------|
| Bealli Design                 |   |          |  |   | 2023A2            |
| <sup>Engr.</sup> N. Wilkerson | MEDEEK ENGINE   |          |  | This report may not be<br>copied, reproduced or<br>distributed without the<br>written consent of<br>Medeek Engineering Inc. | Rev.              |
| Date 1/12/2023                | 3050 State Route 109 Copa<br>ph. (425) 741-5555 www.n |          |  | Copyright © 2014  | Page 2            |


$$\rho_w = 62.4 \left[ \frac{0.55}{1 + 0.55(0.009)(19)} \right] \left[ 1 + \frac{19}{100} \right] = 37.33 \text{ lbs/ft}^3$$


 $\begin{aligned} \text{Volume}_{\text{total}} &= \text{N}[\text{A x } (\text{L} + \text{l}_{\text{b}})] = 2 \text{ x } [13.88 \text{ x } (141.00 + 3)] \text{ x } (12 \text{ in./ft.})^3 = 2.31 \text{ ft}^3 \\ \text{Volume}_{\text{span}} &= \text{N}[\text{A x } \text{L}] = 2 \text{ x } [13.88 \text{ x } 141.00] \text{ x } (12 \text{ in./ft.})^3 = 2.26 \text{ ft}^3 \end{aligned}$ 

Total Weight (W<sub>T</sub>) =  $\rho_W x$  Volume<sub>total</sub> = 37.33 x 2.31 = 86.3 lbs Self Weight (W<sub>S</sub>) =  $\rho_W x$  Volume<sub>span</sub> = 37.33 x 2.26 = 84.5 lbs

Distributed Self Weight (w<sub>s</sub>) =  $\frac{W_S}{L} = \frac{84.5}{11.75}$  = 7.19 plf

Load, Shear and Moment Diagrams:





### 1.) Bending:

Members subject to bending stresses shall be proportioned so that the actual bending stress or moment shall not exceed the adjusted bending design value:

 $f_b \leq F_b' \ (\textit{NDS Sec. 3.3.1})$ 

where:

$$\label{eq:fb} \begin{split} f_b &= M \ / \ S \\ F_b' &= F_b(C_D)(C_M)(C_t)(C_L)(C_F)(C_i)(C_r) \end{split}$$

Beam is braced laterally along its compression edge. Laterial stability is not a consideration:

 $C_L$  = Beam Stability Factor = 1.0

 $F_{bx}' = (800)(1.15)(1)(1)(1)(1)(1)(1)(1) = 920.0 \text{ psi}$ 

$$\mathbf{f_b} = \frac{M}{N \times S_x} = \frac{37731}{2 \times 21.39} = 882.0 \text{ psi}$$

$$f_b = 882.0 \text{ psi} < F_{bx}' = 920.0 \text{ psi} (CSI = 0.96)$$
 ? **OK**

| Subject<br>Beam Design | Customer  | Location |  |   | Job No.<br>2023A2 |
|------------------------|---|----------|--|---|-------------------|
| Engr.<br>N. Wilkerson  | MEDEEK ENGINE   |          |  | This report may not be<br>copied, reproduced or<br>distributed without the<br>written consent of<br>Medeek Engineering Inc. | Rev.              |
| Date 1/12/2023         | 3050 State Route 109 Copa<br>ph. (425) 741-5555 www.r |          |  | Copyright © 2014  | Page 4            |

#### 2.) Shear:

Members subject to shear stresses shall be proportioned so that the actual shear stress parallel to grain or shear force at any cross section of the bending member shall not exceed the adjusted shear design value:

$$f_V \leq F_V'$$
 (NDS Sec. 3.4.1)

where:

$$\mathbf{f_v} = \frac{3V}{2A}$$

 $F_{v}' = F_{v}(C_{D})(C_{M})(C_{t})(C_{i})$ 

$$F_{vx'} = (175)(1.15)(1)(1)(1) = 201.25 \text{ psi}$$

Shear Reduction: For beams supported by full bearing on one surface and loads applied to the opposite surface, uniformly distributed loads within a distance, d, from supports equal to the depth of the bending member shall be pemitted to be ignored. For beams supported by full bearing on one surface and loads applied to the opposite surface, concentrated loads within a distance equal to the depth of the bending member from supports shall be permitted to be multiplied by x/d where x is the distance from the beam support face to the load. See NDS 2015, Figure 3C.

$$f_V * = \frac{3V^*}{2(N \times A)} = \frac{3(929.95)}{2(2 \times 13.88)} = 50.27 \text{ psi}$$

$$f_v^* = 50.27 \text{ psi} < F_{vx'} = 201.25 \text{ psi} (CSI = 0.25)$$
 ? OK

No Reduction in Shear (conservative):

$$\mathbf{f_v} \!=\! \frac{3V}{2(N \times A)} = \frac{3(1070.39)}{2(2 \times 13.88)} \!= \! \mathbf{57.86} \, \mathbf{psi}$$

$$f_v = 57.86 \text{ psi} < F_{vx'} = 201.25 \text{ psi} (CSI = 0.29)$$
 ? **OK**

### 3.) Deflection:

Bending deflections calculated per standard method of engineering mechanics for live load and total load:

#### LL Allowable: L/360 TL Allowable: L/240

 $E_x' = E_x(C_M)(C_t)(C_i) = 1400000(1)(1)(1) = 1400000 \text{ psi}$ 

| Subject<br>Beam Design | Customer  | Location |  |   | Job No.<br>2023A2 |
|------------------------|---|----------|--|---|-------------------|
| N. Wilkerson           | MEDEEK ENGINE   |          |  | This report may not be<br>copied, reproduced or<br>distributed without the<br>written consent of<br>Medeek Engineering Inc. | Rev.              |
| Date 1/12/2023         | 3050 State Route 109 Copalis Beach, WA 98535<br>ph. (425) 741-5555 www.medeek.com |          |  |   | Page 5            |

$$\Delta_{LL} = \frac{5w_{LL}L^4}{384E'_x(N \times I_x)} = \frac{5(100)(11.75)^4}{384(1400000)(2 \times 98.93)} \times \left(12\frac{in.}{ft.}\right)^3 = 0.15 \text{ in.}$$

$$(L/d)_{LL} = 141.00 / 0.15 = 911$$

$$\Delta_{LL} = 0.15 \text{ in} = L/911 < L/360 ? \text{OK}$$

$$\Delta_{TL} = \frac{5(w_{TL} + w_s)L^4}{384E'_x(N \times I_x)} = \frac{5(175 + 7.19)(11.75)^4}{384(1400000)(2 \times 98.93)} \times \left(12\frac{in.}{ft.}\right)^3 = 0.28 \text{ in.}$$

$$(L/d)_{TL} = 141.00 / 0.28 = 500$$

$$\Delta_{TL} = 0.28 \text{ in} = L/500 < L/240 ? \text{OK}$$

#### 4.) Bearing:

Members subject to bearing stresses perpendicular to the grain shall be proportioned so that the actual compressive stress perpendicular to grain shall be based on the net bearing area and shall not exceed the adjusted compression design value perpendicular to grain:

 $f_{c\perp} \leq F_{c\perp}$ ' (NDS Sec. 3.10.2)

where:

$$\mathbf{f_c}_{\perp} = \frac{R}{A_b}$$

 $F_{c\perp}' = F_{c\perp}(C_M)(C_t)(C_i)$ 

 $F_{c \perp x}' = (565)(1)(1)(1) = 565.00 \text{ psi}$ 

$$A_b = b x l_b = 1.5 x 3 = 4.50 in^2$$

$$f_{c\perp} = \frac{R}{N \times A_b} = \frac{1093.16}{2 \times 4.50} = 121.5 \text{ psi}$$

 $f_{c\,\perp} = 121.5 \; psi < F_{c\,\perp\,x'} = 565.00 \; psi \; (CSI = 0.21) \; ? \; \textbf{OK}$ 

\*Disclaimer: The calculations produced herein are for initial design and estimating purposes only. The calculations and drawings presented do not constitute a fully engineered design. All of the potential load cases required to fully design an actual structure may not be provided by this calculator. For the design of an actual structure, a registered and licensed professional should be consulted as per IRC 2012 Sec. R802.10.2 and designed according to the minimum requirements of ASCE 7-10. The beam calculations provided by this online tool are for educational and illustrative purposes only. Medeek Design assumes no liability or loss for any designs presented and does not guarantee fitness for use.

| Subject<br>Beam Design        | Customer  | Location                          |   | Job No.<br>2023A2 |
|-------------------------------|---|-----------------------------------|---|-------------------|
|                               |   |                                   |   | 2025112           |
| <sup>Engr.</sup> N. Wilkerson | MEDEEK ENGINE   |                                   | This report may not be<br>copied, reproduced or<br>distributed without the<br>written consent of<br>Medeek Engineering Inc. | Rev. –            |
| Date 1/12/2023                | 3050 State Route 109 Copa<br>ph. (425) 741-5555 www.n | lis Beach, WA 98535<br>nedeek.com | Copyright © 2014  | Page 6            |